




# DAKOTA GRANITE

## Granite Blocks & Slabs

*The Granite People*  
SINCE 1925



# DAKOTA MAHOGANY®






Dakota Granite® is proud of our domestically produced **Dakota Mahogany®**. Dakota Mahogany® is quarried near Milbank, South Dakota, and continues to be the mahogany granite by which all other granites are measured.

QUARRIED SUSTAINABLY IN MILBANK  
SOUTH DAKOTA



# DAKOTA MAHOGANY®

## BLOCKS

				
<hr/> <b>MONUMENTAL</b>	<hr/> <b>90/10</b>	<hr/> <b>80/20</b>	<hr/> <b>60/40</b>	<hr/> <b>&lt;50/50</b>
<hr/> \$/CUBIC FOOT	<hr/> \$/CUBIC FOOT	<hr/> \$/CUBIC FOOT	<hr/> \$/CUBIC FOOT	<hr/> \$/CUBIC FOOT
<hr/> \$55.25	<hr/> \$48	<hr/> \$39	<hr/> \$29.50	<hr/> \$20.50

*\*FRACTIONS REPRESENT CONDITON OF SLAB*

*For example a 90/10 slab would be 90% clear and 10% having either a streak, seam or broken corner.*



# DAKOTA MAHOGANY®

## SLABS

### MONUMENTAL

THICKNESS	\$/SQ FT
-----------	----------

4"	\$28
----	------

6"	\$38.50
----	---------

8"	\$48
----	------

12"	\$66.50
-----	---------

### 90/10

THICKNESS	\$/SQ FT
-----------	----------

4"	\$26.50
----	---------

6"	\$35.25
----	---------

8"	\$44.25
----	---------

12"	\$62
-----	------

### 80/20

THICKNESS	\$/SQ FT
-----------	----------

4"	\$24
----	------

6"	\$30.25
----	---------

8"	\$39
----	------

12"	\$53.75
-----	---------

*\*FRACTIONS REPRESENT CONDITON OF SLAB*

*For example a 90/10 slab would be 90% clear and 10% having either a streak, seam or broken corner.*



# DAKOTA MAHOGANY®

## TEST DATA

### **ASTM C 97**

DENSITY..... 167 LBS/FT3

ABSORPTION..... 0.14 %

### **ASTM C 170**

COMPRESSIVE STRENGTH..... 21,257 PSI

### **ASTM C 99**

MODULUS OF RUPTURE..... 2,613 PSI

### **ASTM C 241**

ABRASION RESISTANCE..... 57 HA

### **ASTM C 880**


FLEXURAL STRENGTH.....1,598 PSI



# SUPERIOR BLACK

**Superior Black is one of our most popular granites.** It is a medium black granite with a medium-grained texture that sandblasts and contrasts nicely. Superior Black is quarried in Minnesota and is priced competitively.

QUARRIED SUSTAINABLY IN  
NORTHERN MINNESTOA




# SUPERIOR BLACK

## BLOCKS

---

**MONUMENTAL**

CALL FOR PRICING



---

**90/10**

\$/CUBIC FOOT

---


**\$37.75**

---



*\*FRACTIONS REPRESENT CONDITON OF SLAB*

*For example a 90/10 slab would be 90% clear and 10% having either a streak, seam or broken corner.*



# SUPERIOR BLACK


## SLABS

THICKNESS	\$/SQ FT
4"	\$21.75
6"	\$28.75
8"	\$35
12"	\$47.75



*\*FRACTIONS REPRESENT CONDITON OF BLOCK*

*For example a 90/10 slab would be 90% clear and 10% having either a streak, seam or broken corner.*



# SUPERIOR BLACK

## TEST DATA

### **ASTM C 97**

DENSITY..... 178.1 LBS/FT3

ABSORPTION..... 0.14 %

### **ASTM C 170**

COMPRESSIVE STRENGTH..... 26,800 PSI

### **ASTM C 99**


MODULUS OF RUPTURE.....2,700 PSI

### **ASTM C 241**

ABRASION RESISTANCE..... 28.7 HA

### **ASTM C 880**

FLEXURAL STRENGTH.....2,400 PSI





**Dakota Granite**  
**48391 150th Street**  
**Milbank, South Dakota 57252**

**1-800-843-3333**  
**[www.dakotagranite.com](http://www.dakotagranite.com)**

